

# PVC Schedule 80 Pipe

## PVC Schedule 80 Pipe, Type 1, Grade 1 - Plain End

PVC SCHEDULE 80 (GRAY)			PLAIN END			PVC 1120	
PART NO.	NOM. SIZE	UPC # 611942-	QTY. PER SKID	AVG. OD (IN.)	MIN. WALL (IN.)	MAX WORK PRESSURE AT 23° C OR 73° F	WT. PER 100 FT. (LBS.)
PVC 10002	1/4"x20'	04920	15140'	0.540	.119	1130 PSI	10.0
PVC 10003	3/8"x20'	04917	9360'	0.675	.126	920 PSI	13.8
PVC 10005	1/2"x20'	03968	6880'	0.840	.147	850 PSI	20.3
PVC 10007	3/4"x20'	03969	4200'	1.050	.154	690 PSI	27.5
PVC 10010	1"x20'	03970	3540'	1.315	.179	630 PSI	40.5
PVC 10012	1 1/4"x20'	03973	4240'	1.660	.191	520 PSI	55.9
PVC 10015	1 1/2"x20'	03976	3440'	1.900	.200	470 PSI	67.7
PVC 10020	2"x20'	03977	1980'	2.375	.218	400 PSI	93.6
PVC 10025	2 1/2"x20'	03978	1360'	2.875	.276	420 PSI	142.8
PVC 10030	3"x20'	03979	960'	3.500	.300	370 PSI	191.1
PVC 10040	4"x20'	03980	1080'	4.500	.337	320 PSI	279.3
PVC 10060	6"x20'	03981	480'	6.625	.432	280 PSI	532.7
PVC 10080	8"x20'	04175	300'	8.625	.500	250 PSI	808.9
PVC 10100	10"x20'	04768	160'	10.750	.593	230 PSI	1199.3
PVC 10120	12"x20'	04770	120'	12.750	.687	230 PSI	1650.1
PVC 10140	14"x20'	04816	60'	14.000	.750	220 PSI	1930.0
PVC 10160	16"x20'	04919	60'	16.000	.843	220 PSI	2544.1

Note: Full pallets are polyethylene wrapped for cleanliness and UV protection.

NSF Listed. Meets All Requirements of ASTM D 1784 and ASTM D 1785.



## WARNING

Testing with or use of compressed air or gas in PVC / ABS / CPVC pipe or fittings can result in explosive failures and cause severe injury or death.

AIR/GAS



- NEVER test with or transport/store compressed air or gas in PVC / ABS / CPVC pipe or fittings.
- NEVER test PVC / ABS / CPVC pipe or fittings with compressed air or gas, or air over water boosters.
- ONLY use PVC / ABS / CPVC pipe for water or approved chemicals.
- Refer to warnings in PPFA User Bulletin 4-80 and ASTM D 1785.