

PVC Pipe: Schedule 40



>> PVC Schedule 40 Pipe - Plain End

PVC SCHEDULE 40 (WHITE)		PLAIN END		PVC 1120	ASTM D 1785	
PART NO.	NOM. SIZE	UPC # 611942-	AVG. OD (IN.)	MIN. WALL (IN.)	MAX WORK PRESSURE AT 23° C OR 73° F	WT. PER 100 FT. (LBS.)
PVC 4005	1/2" x 10'	06658	.840	.109	600 PSI	15.9
PVC 4005	1/2" x 20'	03922	.840	.109	600 PSI	15.9
PVC 4007	3/4" x 10'	06661	1.050	.113	480 PSI	21.1
PVC 4007	3/4" x 20'	03925	1.050	.113	480 PSI	21.1
PVC 4010	1" x 10'	06664	1.315	.133	450 PSI	31.3
PVC 4010	1" x 20'	03928	1.315	.133	450 PSI	31.3
PVC 7100*	1 1/4" x 10'	03945	1.660	.140	370 PSI	42.4
PVC 7100*	1 1/4" x 20'	03946	1.660	.140	370 PSI	42.4
PVC 7112*	1 1/2" x 10'	03947	1.900	.145	330 PSI	50.7
PVC 7112*	1 1/2" x 20'	03948	1.900	.145	330 PSI	50.7
PVC 7200*	2" x 10'	03949	2.375	.154	280 PSI	68.1
PVC 7200*	2" x 20'	03950	2.375	.154	280 PSI	68.1
PVC 4025‡	2 1/2" x 20'	04205	2.875	.203	300 PSI	108.0
PVC 7300*	3" x 10'	03951	3.500	.216	260 PSI	141.2
PVC 7300*	3" x 20'	03952	3.500	.216	260 PSI	141.2
PVC 7400†	4" x 10'	03953	4.500	.237	220 PSI	201.2
PVC 7400†	4" x 20'	03954	4.500	.237	220 PSI	201.2
PVC 7500†	5" x 20'	04837	5.563	.258	190 PSI	272.5
PVC 7600†	6" x 10'	03955	6.625	.280	180 PSI	353.7
PVC 7600†	6" x 20'	03956	6.625	.280	180 PSI	353.7
PVC 7800†	8" x 20'	03958	8.625	.322	160 PSI	532.3
PVC 7910†	10" x 20'	03959	10.750	.365	140 PSI	754.7
PVC 7912†	12" x 20'	03961	12.750	.406	130 PSI	997.9
PVC 7914†	14" x 20'	04862	14.000	.437	130 PSI	1180.1
PVC 7916†	16" x 20'	04918	16.000	.500	130 PSI	1543.1

* Dual Marked ASTM D 1785 and ASTM D 2665.

† Triple Marked ASTM D 1785 & ASTM D 2665 & ASTM F 480.

‡ Dual Marked ASTM D 1785 & ASTM F 480.

NOTE: When ordering, please specify plain end or bell end.

NSF Listed. Meets All Requirements of ASTM D 1784 and ASTM D 1785.

⚠ WARNING

Testing with or use of compressed air or gas in PVC / ABS / CPVC pipe or fittings can result in explosive failures and cause severe injury or death.

AIR/GAS

- NEVER test with or transport/store compressed air or gas in PVC / ABS / CPVC pipe or fittings.
- NEVER test PVC / ABS / CPVC pipe or fittings with compressed air or gas, or air over water boosters.
- ONLY use PVC / ABS / CPVC pipe for water or approved chemicals.
- Refer to warnings in PPFA User Bulletin 4-80 and ASTM D 1785.